Electroformed Nickel Mirrors for NGST


John Redmon NASA/MSFC

NGST TECHNOLOGY CHALLENGE GSFC July 7-10,1997


Contents:

- NGST Primary Mirror Point Design
- Replication Process
- Prototype Mirrors
- Future Plans


Optical Telescope Assembly



TYPICAL LONGITUDINAL SECTION



TYPICAL SECTION AT SEGMENT ACTUATORS (VIEWED IN THE RADIAL DIRECTION)



Sectional Views of Typical Petal

Mirror Requirements


- Deployed Primary Mirror
- Phase Adjustment on Primary Segments
- Lightweight Construction (15kg/m2)
- Deformable Quartenary
- 60 Kelvin Operation


Nickel Replication


- Nickel Electroforms can be fabricated in <u>very</u> low stress forms
- Complex Shapes (stiffeners, ribs, etc.)
- 70ksi YS
- Wall thickness down to 0.5 mils
- Structures, Flexures, Mounting Provisions, etc., can be plated to the optic
- Excellent Surface Finish (< 10 Angstroms)
- Thickness variation less than 2%
- Untested Cryogenic Performance


Replication Applied to Normal Incidence Optics


- 1. Machine
- 2. Single-Point Diamond Turn
- 3. Electroless Nickel Plate













5. Polish




6. Apply reflective layer




7. Electroform



8. Separate



NGST 4/16/96



Electroforming Bath



PROPOSED

CENTER OF EXCELLENCE FOR SPACE OPTICS




George C. Marshall Space Flight Center






Replicated Optics



Half Meter NGST Prototype



NGST

REPLICATED OPTICS


Nickel Replication

- Build subscale mirror configuration
- Test


Figure and Surface Quality
Thermal Hysteresis

Plating Parameters
Vibro-acoustic


60 Kelvin Optical Test at JPL




TYPICAL SECTION AT ACTUATOR



Half Meter Prototype






Prototype Status

- First half-meter nickel mirror produced on 6/30/97
- Graphite Epoxy Structure Complete
- Flexure Plating trials underway
- Room temperature metrology and hysteresis testing underway
- 60 K Optical Test





I



Nation in Aeronautics and Space Administration

Future Plans

- Larger Mirrors (1 meter plus)
- Design Options
 Ribs, Flexures, etc.
- Tooling and Process
 Enhanced Stress Gage
 Mandrel "Cambering"
- Alloying
 Additions of Cobalt and/or Iron

Future Plans

- Larger Mirrors (1 meter plus)
- Design Options Ribs, Flexures, etc.
- Tooling and Process
 Enhanced Stress Gage
 Mandrel "Cambering"
- Alloying
 Additions of Cobalt and/or Iron

Acknowledgments:

- Bill Jones, Howard Hall, Charlie Griffith, Roger Underdaul, Gary Thornton, Joe Mirandy/NASA/MSFC/Astrionics Lab
- Darrell Engelhaupt/University of Alabama in Huntsville, Center of Applied Optics
- Mitch Mendrek, Patricia Johnson, Steve Hudson, John Vickers/NASA/MSFC/ Materials and Processes Laboratory